


LT-S901 | Pentacene


Pentacene

CAS No. : 135-48-8
 Grade : Sublimed >99%
 TGA : >290 °C (0.5% wt. loss)
 Formula : $C_{22}H_{14}$
 M.W. : 278.35 g/mole
 UV : 300 nm (in CH_2Cl_2)
 PL : 509 nm (in CH_2Cl_2)

**LT-S902** | PDCDT


N,N'-Bis(2,5-di-tert-butylphenyl)-3,4,9,10-perylene dicarboximide

CAS No. : 83054-80-2
 Grade : Sublimed >99%
 TGA : >350 °C (0.5% wt. loss)
 Formula : $C_{52}H_{50}N_2O_4$
 M.W. : 766.96 g/mole
 UV : 524 nm (in CH_2Cl_2)
 PL : 544, 574 nm (in CH_2Cl_2)

**LT-S904** | PenPTC

N,N'-Dipentyl-3,4,9,10-perylene dicarboximide

CAS No. : 76372-75-3
 Grade : Sublimed >99%
 TGA : >350 °C (0.5% wt. loss)
 Formula : $C_{34}H_{30}N_2O_4$
 M.W. : 530.61 g/mole
 UV : 523 nm (in CH_2Cl_2)
 PL : 535, 573 nm (in CH_2Cl_2)

**LT-S918** | PTCBI


Bisbenzimidazo[2,1-a:1',2'-b']anthra[2,1,9-def:6,5,10-d'e'f'] diisoguinoline-10,21-dione, with cis isomer

CAS No. : 79534-91-1
 Grade : Sublimed >99%
 TGA : >420 °C (0.5% wt. loss)
 Formula : $C_{36}H_{16}N_4O_2$
 M.W. : 536.54 g/mole
 PL : 414 nm (in CH_2Cl_2)

**LT-S919** | ADIDI


Anthra[2'',1'',9'':4,5,6,6',5',10'':4',5',6']diisouino[2,1-a:2',1'-a'] diperimidine-12,25-dione, with cis isomer

CAS No. : 6859-32-1
 Grade : Sublimed >99%
 TGA : >430 °C (0.5% wt. loss)
 Formula : $C_{44}H_{20}N_4O_2$
 M.W. : 636.66 g/mole
 PL : 413 nm (in CH_2Cl_2)

**LT-S920** | PTCDA


3,4,9,10-Perylenetetracarboxylic dianhydride

CAS No. : 128-69-8
 Grade : Sublimed >99%
 TGA : >450 °C (0.5% wt. loss)
 Formula : $C_{24}H_6O_6$
 M.W. : 392.32 g/mole
 PL : 413 nm (in CH_2Cl_2)

**LT-S921** | PTCDI


3,4,9,10-Perylenetetracarboxylic diimide

CAS No. : 81-33-4
 Grade : Sublimed >99%
 TGA : >450 °C (0.5% wt. loss)
 Formula : $C_{24}H_{10}N_2O_4$
 M.W. : 390.35 g/mole
 PL : 413 nm (in CH_2Cl_2)

**LT-S924** | NTCDA


1,4,5,8-Naphthalenetetracarboxylic dianhydride

CAS No. : 81-30-1
 Grade : Sublimed >99%
 Formula : $C_{14}H_6O_6$
 M.W. : 268.18 g/mole
 UV : 366 nm (in CH_2Cl_2)
 PL : 394 nm (in CH_2Cl_2)

**LT-S925** | MePTC


N,N'-Dimethyl-3,4,9,10-perylene dicarboximide

CAS No. : 5521-31-3
 Grade : Sublimed >99%
 TGA : >440 °C (0.5% wt. loss)
 Formula : $C_{26}H_{14}N_2O_4$
 M.W. : 418.4 g/mole
 UV : 522 nm (in CH_2Cl_2)
 PL : 571 nm (in CH_2Cl_2)

**LT-S926** | HepPTC


N,N'-Diheptyl-3,4,9,10-perylene dicarboximide

CAS No. : 95689-91-1
 Grade : Sublimed >99%
 TGA : >390 °C (0.5% wt. loss)
 Formula : $C_{38}H_{38}N_2O_4$
 M.W. : 586.72 g/mole
 UV : 524 nm (in CH_2Cl_2)
 PL : 537, 571 nm (in CH_2Cl_2)

**LT-S928** | F₁₆CuPC


Copper(II) 1,2,3,4,8,9,10,11,15,16,17,18,22,23,24,25-hexadecafluoro-29H,31H-phthalocyanine

CAS No. : 14916-87-1
 Grade : Sublimed product
 Formula : $C_{32}F_{16}CuN_8$
 M.W. : 863.92 g/mole
 UV : 690 nm (in CH_2Cl_2)

**LT-S935** | 4CIPEPTC


N,N'-Bis[2-(4-chloro-phenyl)-ethyl]-3,4,9,10-perylene dicarboximide

CAS No. : 215726-51-5
 Grade : Sublimed >99%
 TGA : >370 °C (0.5% wt. loss)
 Formula : $C_{40}H_{24}Cl_2N_2O_4$
 M.W. : 667.53 g/mole
 UV : 524 nm (in CH_2Cl_2)
 PL : 544 nm (in CH_2Cl_2)




LT-S936 | 4FPEPTC


N,N'-Bis[2-(4-fluoro-phenyl)-ethyl]-3,4,9,10-perylene dicarboximide
 CAS No. : 215726-57-1
 Grade : Sublimed >99%
 TGA : >370 °C (0.5% wt. loss)
 Formula : $C_{40}H_{24}F_2N_2O_4$
 M.W. : 634.63 g/mole
 UV : 524 nm (in CH_2Cl_2)
 PL : 538 nm (in CH_2Cl_2)

**LT-S937** | 24CIPEPTC


N,N'-Bis[2-(2,4-dichloro-phenyl)-ethyl]-3,4,9,10-perylene dicarboximide
 Grade : Sublimed >99%
 TGA : >390 °C (0.5% wt. loss)
 Formula : $C_{40}H_{22}Cl_4N_2O_4$
 M.W. : 736.42 g/mole
 UV : 524 nm (in CH_2Cl_2)
 PL : 536 nm (in CH_2Cl_2)

**LT-S938** | 26CIPEPTC


N,N'-Bis[2-(2,6-dichloro-phenyl)-ethyl]-3,4,9,10-perylene dicarboximide
 Grade : Sublimed >99%
 TGA : >440 °C (0.5% wt. loss)
 Formula : $C_{40}H_{22}Cl_4N_2O_4$
 M.W. : 736.42 g/mole
 UV : 524 nm (in CH_2Cl_2)
 PL : 536 nm (in CH_2Cl_2)

**LT-S939** | PEPTC


N,N'-Bis(2-phenyl-ethyl)-3,4,9,10-perylene dicarboximide
 CAS No. : 67075-37-0
 Grade : Sublimed >99%
 TGA : >390 °C (0.5% wt. loss)
 Formula : $C_{40}H_{26}N_2O_4$
 M.W. : 598.64 g/mole
 UV : 524 nm (in CH_2Cl_2)
 PL : 537 nm (in CH_2Cl_2)

**LT-S940** | Tetracene


2,3-Benzanthracene
 CAS No. : 92-24-0
 Grade : Sublimed >99%
 TGA : >180 °C (0.5% wt. loss)
 Formula : $C_{18}H_{12}$
 M.W. : 228.29 g/mole
 UV : 277 nm (in CH_2Cl_2)
 PL : 514 nm (in CH_2Cl_2)

**LT-S941** | DP-PTCDI


N,N'-Diphenyl-3,4,9,10-perylene dicarboximide
 CAS No. : 128-65-4
 Grade : Sublimed >99%
 TGA : >380 °C (0.5% wt. loss)
 Formula : $C_{36}H_{18}N_2O_4$
 M.W. : 542.54 g/mole
 UV : 481, 515 nm (in THF)
 PL : 531 nm (in THF)

**LT-S956** | PDI1


N,N'-Bis(3,4,5-tridodecyloxyphenyl)-3,4,9,10-perylene dicarboximide
 CAS No. : 351377-40-7
 Grade : >99% (NMR)
 TGA : >290 °C (0.5% wt. loss)
 Formula : $C_{108}H_{162}N_2O_{10}$
 M.W. : 1648.45 g/mole
 UV : 489, 526 nm (in CH_2Cl_2)

**LT-S960** | 4MeOPEPTC

N,N'-Bis[2-(4-methoxyphenyl)-ethyl]-3,4,9,10-perylene dicarboximide
 CAS No. : 119215-14-4
 Grade : Sublimed >99%
 TGA : >370 °C (0.5% wt. loss)
 Formula : $C_{42}H_{30}N_2O_6$
 M.W. : 658.70 g/mole
 UV : 458, 524 nm (in CH_2Cl_2)
 PL : 534 nm (in CH_2Cl_2)

**LT-S968** | 6,13-DP-Penta

6,13-Diphenylpentacene
 CAS No. : 76727-11-2
 Grade : Sublimed >99% (HPLC)
 TGA : >250 °C (0.5% wt. loss)
 Formula : $C_{34}H_{22}$
 M.W. : 430.54 g/mole
 UV : 307 nm (in CH_2Cl_2)
 PL : 447 nm (in CH_2Cl_2)



LT-S969 | **α-6T***α*-Sexithiophene


CAS No. : 88493-55-4

Grade : Sublimed >99%

TGA : >330 °C (0.5% wt. loss)

Formula : C₂₄H₁₄S₆

M.W. : 494.76 g/mole

UV : 437 nm (in CH₂Cl₂)PL : 511 nm (in CH₂Cl₂)**LT-S970** | **PTCDI-C₈***N,N'*-Dioctyl-3,4,9,10-perylene dicarboximide


CAS No. : 78151-58-3

Grade : Sublimed >99%

TGA : >390 °C (0.5% wt. loss)

Formula : C₄₀H₄₂N₂O₄

M.W. : 614.77 g/mole

UV : 456, 524 nm (in CH₂Cl₂)PL : 573 nm (in CH₂Cl₂)**LT-S972** | **αω-DH6T**

5,5'-Dihexyl-2,2':5',2'':5'',2''':5''',2''''-sexithiophene

CAS No. : 151271-43-1


Grade : Sublimed >99%

TGA : >230 °C (0.5% wt. loss)

Formula : C₃₆H₃₈S₆

M.W. : 663.08 g/mole

PL : 439 nm (in Toluene)

**LT-S973** | **TCNQ**

7,7,8,8-Tetracyanoquinodimethane


CAS No. : 1518-16-7

Grade : Sublimed >99%

TGA : >210 °C (0.5% wt. loss)

Formula : C₁₂H₄N₄

M.W. : 204.19 g/mole

UV : 259, 404 nm (in CH₂Cl₂)**LT-S975** | **FTTF**

5,5'-Di(9H-fluoren-2-yl)-2,2'-bithiophene

CAS No. : 369599-41-7


Grade : Sublimed >99%

TGA : >200 °C (0.5% wt. loss)

Formula : C₃₄H₂₂S₂

M.W. : 494.67 g/mole

PL : 378 nm (in Toluene)

**LT-S976** | **DH-FTTF**

5,5'-Bis(7-hexyl-9H-fluoren-2-yl)-2,2'-bithiophene

CAS No. : 369599-42-8


Grade : Sublimed >99%

TGA : >200 °C (0.5% wt. loss)

Formula : C₄₆H₄₆S₂

M.W. : 662.99 g/mole

UV : 378 nm (in Toluene)

**LT-S977** | **TIPS**

6,13-Bis(triisopropylsilyl)ethynyl)pentacene


CAS No. : 373596-08-8

Grade : >99%

TGA : >230 °C (0.5% wt. loss)

Formula : C₄₄H₅₄Si₂

M.W. : 639.07 g/mole

UV : 307 nm (in CH₂Cl₂)**LT-S8014** |


5,5'-Diphenyl-2,3-dihydro-2,2':5',2'':5'',2''':5''',2''''-quaterthiophene

CAS No. : 238397-97-2

Grade : Sublimed >99%

Formula : C₂₈H₂₀S₄

M.W. : 484.72 g/mole

**LT-S8020** | **AC5-CF3**


1,4-Bis(5-(4-(trifluoromethyl)phenyl)thiophen-2-yl)benzene

CAS No. : 937185-54-1

Grade : Sublimed >98%

Formula : C₂₈H₁₆F₆S₂

M.W. : 530.55 g/mole

**LT-S8026** | **AC-5**


1,4-Bis(5-phenylthiophen-2-yl)benzene

CAS No. : 256342-39-9

Grade : Sublimed >99%

Formula : C₂₆H₁₈S₂

M.W. : 394.55 g/mole



LT-S8038


6,13-Bis((triisopropylsilyl)ethynyl)quinoxalino[2,3-b]phenazine

CAS No. : 1169703-65-4

Grade : >98%

Formula : $C_{40}H_{50}N_4Si_2$

M.W. : 643.02 g/mole



LT-S8045 dNaAnt


2,6-Di(2-naphthyl)anthracene

CAS No. : 1086103-31-2

Grade : Sublimed >99%

Formula : $C_{34}H_{22}$

M.W. : 430.54 g/mole



LT-S9026 ADT

Anthra[2,3-b:6,7-b']dithiophene


CAS No. : 144413-58-1

Grade : Sublimed >99%

TGA : >250 °C (0.5% wt. loss)

Formula : $C_{18}H_{10}S_2$

M.W. : 290.40 g/mole

UV : 320 nm (in CH_2Cl_2)

LT-S9027 diF-TES-ADT

2,8-Difluoro-5,11-bis(triethylsilyl)ethynylanthradithiophene, mixture of syn & anti isomers


CAS No. : 1015071-21-2

Grade : >99% (NMR)

TGA : >230 °C (0.5% wt. loss)

Formula : $C_{34}H_{36}F_2S_2Si_2$

M.W. : 602.95 g/mole



LT-S9034 TES-ADT

5,11-Bis(triethylsilyl)ethynylanthradithiophene, mixture of syn & anti isomers


CAS No. : 851817-11-3

Grade : >99% (NMR)

TGA : >230 °C (0.5% wt. loss)

Formula : $C_{34}H_{38}S_2Si_2$

M.W. : 566.97 g/mole

UV : 306 nm (in CH_2Cl_2)

LT-S9035 DPT

5,12-Diphenyltetracene


CAS No. : 27130-32-1

Grade : Sublimed >99%

TGA : >230 °C (0.5% wt. loss)

Formula : $C_{30}H_{20}$

M.W. : 380.48 g/mole

UV : 262, 492 nm (in CH_2Cl_2)

LT-S9036 DIP

Diindeno[1,2,3-cd:1',2'-lm]perylene


CAS No. : 188-94-3

Grade : Sublimed product

TGA : >230 °C (0.5% wt. loss)

Formula : $C_{32}H_{16}$

M.W. : 400.47 g/mole

UV : 494, 532 nm (in CH_2Cl_2)LT-S9041 PTCDI- $C_{18}H_{37}$

N,N'-Dioctadecyl-3,4,9,10-perylenedicarboximide

CAS No. : 25834-02-0


Grade : Sublimed >99%

TGA : >340 °C (0.5% wt. loss)

Formula : $C_{60}H_{82}N_2O_4$

M.W. : 895.30 g/mole

UV : 485, 520 nm (in Toluene)

LT-S9042 PTCDI- $C_{13}H_{27}$

N,N'-Ditridecyl-3,4,9,10-perylenedicarboximide

CAS No. : 95689-92-2


Grade : Sublimed >99%

TGA : >390 °C (0.5% wt. loss)

Formula : $C_{50}H_{62}N_2O_4$

M.W. : 755.04 g/mole

UV : 484, 520 nm (in Toluene)



LT-S9043 Ddodec-FTTF

5,5'-Bis(7-dodecyl-9H-fluoren-2-yl)-2,2'-bithiophene


CAS No. : 846542-27-6

Grade : Sublimed >99%

TGA : >350 °C (0.5% wt. loss)


Formula : $C_{58}H_{70}S_2$

M.W. : 831.31 g/mole


UV : 254, 409 nm (in CH_2Cl_2)

LT-S9049 | 24-FPEPTC


N,N'-Bis[2-(2,4-difluoro-phenyl)-ethyl]-3,4,9,10-perylene dicarboximide
 CAS No. : 1644439-37-1
 Grade : Sublimed >99%
 TGA : >340 °C (0.5% wt. loss)
 Formula : $C_{40}H_{22}F_4N_2O_4$
 M.W. : 670.61 g/mole
 UV : 245 nm (in CH_2Cl_2)

**LT-S9057** | DFH-4T


5,5'-Bis((5-perfluorohexyl)thiophen-2-yl)-2,2'-bithiophene
 CAS No. : 446043-85-2
 Grade : Sublimed >99%
 TGA : >220 °C (0.5% wt. loss)
 Formula : $C_{28}H_8F_{16}S_4$
 M.W. : 966.58 g/mole
 UV : 259, 404 nm (in CH_2Cl_2)

**LT-S9059** | TEPTC


N,N'-Di(thiophen-2-yl)ethyl-3,4,9,10-perylene dicarboximide
 CAS No. : 1559069-50-9
 Grade : Sublimed >99%
 TGA : >400 °C (0.5% wt. loss)
 Formula : $C_{36}H_{22}N_2O_4S_2$
 M.W. : 610.70 g/mole
 UV : 260 nm (in CH_2Cl_2)

**LT-S9077** | BOBTP


1,6-Bis(5'-octyl-2,2'-bithiophen-5-yl)pyrene
 CAS No. : 1430207-54-7
 Grade : Sublimed >99% (NMR)
 Formula : $C_{48}H_{50}S_4$
 M.W. : 755.17 g/mole
 UV : 322, 410 nm (in $CHCl_3$)

**LT-S9080** | DCP


6,13-Dichloropentacene
 CAS No. : 59156-92-2
 Grade : Sublimed >99%
 TGA : >350 °C (0.5% wt. loss)
 Formula : $C_{22}H_{12}Cl_2$
 M.W. : 347.24 g/mole

**LT-S9088** | 5,12-DBTT


5,12-Bis(benzo[b]thiophen-2-yl)tetracene
 CAS No. : 1225220-87-0
 Grade : Sublimed >98%
 Formula : $C_{34}H_{20}S_2$
 M.W. : 492.65 g/mole

**LT-S9092** | 3PenPTC


N,N'-Bis(ethylpropyl)perylene-3,4,9,10-tetracarboxylicdiimide
 CAS No. : 110590-81-3
 Grade : Sublimed >99%
 TGA : >270 °C (0.5% wt. loss)
 Formula : $C_{34}H_{30}N_2O_4$
 M.W. : 530.61 g/mole

**LT-S9093** | DCyPTC


N,N'-Dicyclohexylperylene-3,4,9,10-tetracarboxylicdiimide
 CAS No. : 41572-86-5
 Grade : Sublimed >99%
 TGA : >350 °C (0.5% wt. loss)
 Formula : $C_{36}H_{30}N_2O_4$
 M.W. : 554.63 g/mole

**LT-S9094** | NTDA-C6H13


2,7-Dihexylbenzo[Imn][3,8]phenanthroline-1,3,6,8(2H,7H)-tetraone
 CAS No. : 23536-15-4
 Grade : Sublimed >99% (HPLC)
 TGA : >250 °C (0.5% wt. loss)
 Formula : $C_{26}H_{30}N_2O_4$
 M.W. : 434.53 g/mole

**LT-S9095** | NTDA-C8H17

2,7-Dioctylbenzo[Imn][3,8]phenanthroline-1,3,6,8(2H,7H)-tetraone
 CAS No. : 34155-21-0
 Grade : Sublimed >99% (HPLC)
 TGA : >280 °C (0.5% wt. loss)
 Formula : $C_{30}H_{38}N_2O_4$
 M.W. : 490.63 g/mole

**LT-S9096** | DCyNTDA

2,7-Dicyclohexylbenzo[Imn][3,8]phenanthroline-1,3,6,8(2H,7H)-tetraone
 CAS No. : 173409-43-3
 Grade : Sublimed >99% (HPLC)
 TGA : >280 °C (0.5% wt. loss)
 Formula : $C_{26}H_{26}N_2O_4$
 M.W. : 430.50 g/mole



LT-S9097 | DPNTDA

2,7-Diphenylbenzo[Imn][3,8]phenanthroline-1,3,6,8(2H,7H)-tetraone


CAS No. : 24259-89-0

Grade : Sublimed >99%

TGA : >280 °C (0.5% wt. loss)

Formula : $C_{26}H_{14}N_2O_4$

M.W. : 418.40 g/mole

**LT-S9098** | NTDA- C_5H_{11}

2,7-Dipentylbenzo[Imn][3,8]phenanthroline-1,3,6,8(2H,7H)-tetraone


CAS No. : 173409-41-1

Grade : Sublimed >99% (HPLC)

TGA : >240 °C (0.5% wt. loss)

Formula : $C_{24}H_{26}N_2O_4$

M.W. : 406.47 g/mole

**LT-S9099** | NTDA- C_7H_{15}

2,7-Diheptylbenzo[Imn][3,8]phenanthroline-1,3,6,8(2H,7H)-tetraone


CAS No. : 698370-78-4

Grade : Sublimed >99%

TGA : >280 °C (0.5% wt. loss)

Formula : $C_{28}H_{34}N_2O_4$

M.W. : 462.58 g/mole

**LT-S9100** | NTDA- $C_{13}H_{27}$

2,7-Ditridecylbenzo[Imn][3,8]phenanthroline-1,3,6,8(2H,7H)-tetraone


CAS No. : 1373274-00-0

Grade : Sublimed >99%

TGA : >280 °C (0.5% wt. loss)

Formula : $C_{40}H_{38}N_2O_4$

M.W. : 630.90 g/mole

**LT-S9101** | NTDA- $C_{18}H_{37}$

2,7-Dioctadecylbenzo[Imn][3,8]phenanthroline-1,3,6,8(2H,7H)-tetraone


CAS No. : 144742-50-7

Grade : Sublimed >99% (HPLC)

TGA : >280 °C (0.5% wt. loss)

Formula : $C_{50}H_{78}N_2O_4$

M.W. : 771.17 g/mole

**LT-S9102** | DTT-12

2,6-Bis(4-dodecylphenyl)-dithieno[3,2-b:2',3'-d]thiophene


CAS No. : 1446140-70-0

Grade : Sublimed >99% (NMR)

TGA : >280 °C (0.5% wt. loss)

Formula : $C_{44}H_{60}S_3$

M.W. : 685.14 g/mole

**LT-S9103** | DTT-8

2,6-Bis(4-octylphenyl)-dithieno[3,2-b:2',3'-d]thiophene


CAS No. : 1429377-95-6

Grade : Sublimed >99%

TGA : >270 °C (0.5% wt. loss)

Formula : $C_{36}H_{44}S_3$

M.W. : 572.93 g/mole

**LT-S9128** | Dp-triene-25-CN


(2Z,3E,5Z)-2,5-Dibenzylidenehex-3-enedinitrile

CAS No. : 1376166-32-3

Grade : >99%

Formula : $C_{20}H_{14}N_2$

M.W. : 282.34 g/mole

**LT-S9129** | Dp-tetraene


(1E,3E,5E,7E)-1,8-Diphenylocta-1,3,5,7-tetraene

CAS No. : 3029-40-1

Grade : >99%

Formula : $C_{20}H_{18}$

M.W. : 258.36 g/mole

**LT-S9130** | Dp-pentaene


(1E,3E,5E,7E,9E)-1,10-Diphenyldeca-1,3,5,7,9-pentaene

CAS No. : 3029-41-2

Grade : >99%

Formula : $C_{22}H_{20}$

M.W. : 284.39 g/mole

**LT-S9131** | Dp-triene


(1E,3E,5E)-1,6-Diphenylhexa-1,3,5-triene

CAS No. : 1720-32-7

Grade : >99%

Formula : $C_{18}H_{16}$

M.W. : 232.32 g/mole

**LT-S9132** | PTCPI- $CH_2C_3F_7$

N,N'-Bis(2,2,3,3,4,4,4-heptafluorobutyl)-3,4,9,10-perylene dicarboximide


CAS No. : 1150578-28-1

Grade : Sublimed >99%

TGA : >300 °C (0.5% wt. loss)

Formula : $C_{32}H_{12}F_{14}N_2O_4$

M.W. : 756.44 g/mole

**LT-S9134** | F_4CuPC

Copper(II)-2,9,16,23-tetrafluoro-29H,31H-phthalocyanine


CAS No. : 65602-84-8

Grade : Sublimed >99%

TGA : >350 °C (0.5% wt. loss)

Formula : $C_{32}H_{12}CuF_4N_8$


M.W. : 648.03 g/mole



LT-S9159 | p-Septiphenyl


p-Septiphenyl

CAS No. : 70352-20-4
 Grade : Sublimed >99%
 TGA : >420 °C (0.5% wt. loss)
 Formula : $C_{42}H_{30}$
 M.W. : 534.69 g/mole

**LT-S9171** | F_4ZnPC


Zinc(II)-1,8,15,22-tetrafluoro-29H,31H-phthalocyanine, mixture of isomers

CAS No. : 1120355-28-3
 Grade : Sublimed >99%
 TGA : >300 °C (0.5% wt. loss)
 Formula : $C_{32}H_{12}F_4N_8Zn$
 M.W. : 649.89 g/mole
 UV : 681 nm (in $CHCl_3$)

**LT-S9172** | F_8ZnPC


Zinc(II)-2,3,9,10,16,17,23,24-octafluoro-29H,31H-phthalocyanine

CAS No. : 676519-80-5
 Grade : Sublimed >99%
 TGA : >300 °C (0.5% wt. loss)
 Formula : $C_{32}H_8F_8N_8Zn$
 M.W. : 721.86 g/mole
 UV : 338, 656 nm (in DMF)

**LT-S9173** | An-PDN


2,2'-(9,10-Anthracenediylidene)-bis-propanedinitrile

CAS No. : 70359-39-6
 Grade : Sublimed >99%
 TGA : >250 °C (0.5% wt. loss)
 Formula : $C_{20}H_8N_4$
 M.W. : 304.3 g/mole
 UV : 283, 348 nm (in $CHCl_3$)

**LT-S9174** | DTTCNQ


2,2'-Benzo[1,2-b:4,5-b']dithiophene-4,8-diylidene-bis-propanedinitrile

CAS No. : 109573-90-2
 Grade : Sublimed >99%
 TGA : >250 °C (0.5% wt. loss)
 Formula : $C_{16}H_4N_4S_2$
 M.W. : 316.36 g/mole
 UV : 231, 438 nm (in $CHCl_3$)

**LT-S9175** | 512-TIPS-Tetracene


5,12-Bis((triisopropylsilyl)ethynyl)tetracene

CAS No. : 628316-50-7
 Grade : >99% (HPLC)
 TGA : >250 °C (0.5% wt. loss)
 Formula : $C_{40}H_{52}Si_2$
 M.W. : 589.01 g/mole
 UV : 389 nm (in CH_2Cl_2)

**LT-S9177** | F16FePC


Iron(III) 1,2,3,4,8,9,10,11,15,16,17,18,22,23,24,25-hexadecafluoro-29H,31H-phthalocyanine

CAS No. : 23844-93-1
 Grade : Sublimed >99%
 TGA : >300 °C (0.5% wt. loss)
 Formula : $C_{32}F_{16}FeN_8$
 M.W. : 856.22 g/mole
 UV : 333, 627 nm (in Acetone)

**LT-S9179** | BDT2TH


2,6-Bis[(5'-octyl[2,2'-bithiophene)](4,8-bis(5-octyl-2-thienyl)benzo[1,2-b:4,5-b']dithiophene]

Grade : >99% (NMR)
 Formula : $C_{66}H_{82}S_8$
 M.W. : 1131.88 g/mole
 UV : 249, 359, 442 nm (in $CHCl_3$)

**LT-S9211** | DTT-8


Tribenzo[de,kl,rst]pentaphene

CAS No. : 188-72-7
 Grade : >98% (NMR)
 Formula : $C_{30}H_{16}$
 M.W. : 376.45 g/mole

**LT-S9213** | DPA


2,6-Diphenylanthracene

CAS No. : 95950-70-2
 Grade : Sublimed >99%
 TGA : >200 °C (0.5% wt. loss)
 Formula : $C_{26}H_{18}$
 M.W. : 330.42 g/mole

**LT-S9259**


2,7-Bis(2-(dimethylamino)ethyl)benzo[lmn][3,8]phenanthroline-1,3,6,8(2H,7H)-tetraone

CAS No. : 22291-04-9
 Grade : Sublimed >99% (HPLC)
 Formula : $C_{22}H_{24}N_4O_4$
 M.W. : 408.45 g/mole

**LT-S9260**


4,9-Dibromo-isochromeno[6,5,4-def]isochromene-1,3,6,8-tetraone

CAS No. : 83204-68-6
 Grade : >80%
 Formula : $C_{14}H_2Br_2O_6$
 M.W. : 425.97 g/mole

**LT-S9261**

4,9-Dibromo-2,7-dihexylbenzo[lmn][3,8]phenanthroline-1,3,6,8-tetraone

CAS No. : 1239327-73-1
 Grade : >95%
 Formula : $C_{26}H_{28}Br_2N_2O_4$
 M.W. : 592.32 g/mole




LT-S9262

4,9-Dibromo-2,7-bis(2-ethylhexyl)benzo[Imn][3,8]phenanthroline-1,3,6,8(2H,7H)-tetraone

CAS No. : 1088205-02-0

Formula : $C_{30}H_{36}Br_2N_2O_4$

M.W. : 648.43 g/mole




LT-S9263

4,9-Dibromo-2,7-bis(2-butylloctyl)benzo[Imn][3,8]phenanthroline-1,3,6,8(2H,7H)-tetraone

CAS No. : 1614253-96-1

Formula : $C_{38}H_{52}Br_2N_2O_4$

M.W. : 760.64 g/mole




LT-S9264

4,9-Dibromo-2,7-bis(2-octyldodecyl)benzo[Imn][3,8]phenanthroline-1,3,6,8(2H,7H)-tetraone

CAS No. : 1100243-35-3

Formula : $C_{54}H_{84}Br_2N_2O_4$

M.W. : 985.06 g/mole



LT-S9265


4,9-Dibromo-2,7-bis(2-hexyldecyl)benzo[Imn][3,8]phenanthroline-1,3,6,8(2H,7H)-tetraone

CAS No. : 1459168-68-3

Grade : >98%

Formula : $C_{46}H_{68}Br_2N_2O_4$

M.W. : 872.85 g/mole




LT-S9267

4,5,9,10-Tetrabromo-2,7-dioctylbenzo[Imn][3,8]phenanthroline-1,3,6,8-tetraone

CAS No. : 954374-43-7

Formula : $C_{30}H_{34}Br_4N_2O_4$

M.W. : 806.22 g/mole



LT-S9268 PDIN


2,9-Bis(3-(dimethylamino)propyl)anthra[2,1,9-def:6,5,10-d'e'f']diisoquinoline-1,3,8,10(2H,9H)-tetraone

CAS No. : 117901-97-0

Grade : >97%

Formula : $C_{34}H_{32}N_4O_4$

M.W. : 560.64 g/mole




LT-S9269

5,12-Dibromo-2,9-bis(2-ethylhexyl)anthra[2,1,9-def:6,5,10-d'e'f']diisoquinoline-1,3,8,10(2H,9H)-tetraone

CAS No. : 851786-15-7

Formula : $C_{40}H_{40}Br_2N_2O_4$

M.W. : 772.56 g/mole




LT-S9270

5,12-Dibromo-2,9-bis(2-decyltetradecyl)anthra[2,1,9-def:6,5,10-d'e'f']diisoquinoline-1,3,8,10(2H,9H)-tetraone

CAS No. : 909019-78-9

Formula : $C_{72}H_{104}Br_2N_2O_4$

M.W. : 1221.42 g/mole



LT-S9285 C6-DPA

2,6-Bis(4-hexylphenyl)anthracene


CAS No. : 1258209-99-2

Grade : Sublimed >99%

TGA : >260 °C (0.5% wt. loss)

Formula : $C_{38}H_{42}$

M.W. : 498.74 g/mole



LT-S9500 Bis-HFI-NTCDI

2,7-Di(9H-fluoren-2-yl)benzo[Imn][3,8]-phenanthroline-1,3,6,8(2H,7H)-tetraone


CAS No. : 1397188-84-9

Grade : Sublimed >99%

TGA : >450 °C (0.5% wt. loss)

Formula : $C_{40}H_{22}N_2O_4$

M.W. : 594.61 g/mole



LT-S9538 cis-cis TFT-CN and cis-trans TFT-CN


2,2'-(5Z,5'Z)-5,5'-(furan-2,5-diylidene)bis(4-octylthiophene-5,2(5H)-diylidene)dimalononitrile, mixture of isomers

CAS No. : 1938123-97-7 and 1938123-98-8


Grade : >99% (HPLC)

Formula : $C_{34}H_{38}N_4OS_2$

M.W. : 582.82 g/mole



+



LT-S9540 | TIPS anti DNI


8,16-Bis((triisopropylsilyl)ethynyl)benzo[a]benzo[4,5]-indeno[2,1-h]fluorene

CAS No. : 2080320-19-8

Grade : >99%

Formula : $C_{50}H_{56}Si_2$

M.W. : 713.15 g/mole


**LT-S9548** | BPE-PMDI

2,6-Diphenethylpyrrolo[3,4-f]isoindole-1,3,5,7(2H,6H)-tetraone

Grade : Sublimed >99% :

Formula : $C_{26}H_{20}N_2O_4$

M.W. : 424.45 g/mole


**LT-S9549** | C8-PMDI

2,6-Diethylpyrrolo[3,4-f]isoindole-1,3,5,7(2H,6H)-tetraone

Grade : Sublimed >99% (HPLC)

Formula : $C_{26}H_{26}N_2O_4$

M.W. : 440.58 g/mole


**LT-S9551** | NTDA-C16H33

2,7-Dihexadecylbenzo[Imn][3,8]phenanthroline-1,3,6,8(2H,7H)-tetraone

Grade : Sublimed >99% (HPLC)

Formula : $C_{46}H_{70}N_2O_4$

M.W. : 715.06 g/mole

**LT-S9552** | TIPS-anthracene


9,10-Bis((triisopropylsilyl)ethynyl)anthracene

CAS No. : 862667-06-9

Grade : >99% (HPLC)

Formula : $C_{36}H_{50}Si_2$

M.W. : 538.95 g/mole

**LT-S9553** | DPTTA

2,13-Diphenyl-23,24,25,26-tetrathiapentacyclo-[1 8 2,1,13,6,19,12,14,17]hexacosa-1,3,5,7,9,11,13,15,17,19,21-undecaene


CAS No. : 1265748-61-5

Grade : >99%

Formula : $C_{34}H_{22}S_4$

M.W. : 558.80 g/mole

UV : 319, 401 nm (in Toluene)


**LT-S9554** | C18-PMDI

2,6-Dioctadecylpyrrolo[3,4-f]isoindole-1,3,5,7(2H,6H)-tetraone

Grade : Sublimed >99%

Formula : $C_{46}H_{76}N_2O_4$

M.W. : 721.11 g/mole


**LT-S9561**

2-(5'-(2-Ethylhexyl)-[2,2'-bithiophen]-5-yl)-9H-fluorene-9-one

Grade : >99%

Formula : $C_{29}H_{28}OS_2$

M.W. : 456.66 g/mole

UV : 252, 302 nm (in $CHCl_3$)**LT-S9579** | PDIF-CN2


2,9-Bis(2,2,3,3,4,4,4-heptafluorobutyl)-1,3,8,10-tetraoxo-1,2,3,8,9,10-hexahydroanthra[2,1,9-def:6,5,10-d'e'f]diisoquinoline-5,12-Dicarbonitrile, mixture of isomers

CAS No. : 844868-47-9

Grade : Sublimed >97%

Formula : $C_{34}H_{10}F_{14}N_4O_4$

M.W. : 804.45 g/mole


**LT-S9580** | MT-pyrene

1,3,6,8-Tetrakis(methylthio)pyrene

Grade : Sublimed >99%

Formula : $C_{20}H_{18}S_4$

M.W. : 386.62 g/mole

**LT-S9586** | p-6P


p-Sexiphenyl

CAS No. : 4499-83-6

Grade : Sublimed >99%

Formula : $C_{36}H_{26}$

M.W. : 458.59 g/mole

**LT-S9604** | TIPS-Nph

1,4-Bis((triisopropylsilyl)ethynyl)naphthalene

CAS No. : 2499713-87-8


Grade : >99%

Formula : $C_{32}H_{46}Si_2$

M.W. : 488.89 g/mole

UV : 333 nm (in Toluene)

PL : 588 nm (in Toluene)

**LT-S9605** | BDN


Bis[1-(4-dimethylamino)phenyl-2-phenyl-1,2-ethenedithiolato]nickel(II)

CAS No. : 38465-55-3

Grade : >98%

Formula : $C_{32}H_{30}N_2NiS_4$

M.W. : 629.55 g/mole




LT-S9622 | C10-6T

5,5''''-Didecyl-2,2':5',2'':5'',2''':5''',2''''-sexithiophene

Grade : Sublimed >99%

Formula : $C_{44}H_{54}S_6$

M.W. : 775.29 g/mole

**LT-S9624** | F16TiOPc


Titanium oxide-1,2,3,4,8,9,10,11,15,16,17,18,22,23,24,25-hexadecafluorophthalocyanine

CAS No. : 115537-98-9

Grade : Sublimed >99%

Formula : $C_{32}F_{16}N_8OTi$

M.W. : 864.24 g/mole

**LT-S9640** | CNDSB


(2Z,2'Z)-3,3'-(1,4-phenylene)bis(2-phenylacrylonitrile)

CAS No. : 58393-80-9

Grade : >99%

Formula : $C_{24}H_{16}N_2$

M.W. : 332.4 g/mole

**LT-S9641** | 1,5-DTNA

1,5-Bis((triisopropylsilyl)ethynyl)naphthalene

CAS No. : 2762325-17-5


Grade : >99%

Formula : $C_{32}H_{48}Si_2$

M.W. : 488.89 g/mole

UV : 326 nm (in Toluene)

PL : 554 nm (in Toluene)


**LT-S9642** | NTDA-C4H9

2,7-Dibutylbenzo[Imn][3,8]phenanthroline-1,3,6,8(2H,7H)-tetraone

Grade : Sublimed >99%

Formula : $C_{22}H_{22}N_2O_4$

M.W. : 378.42 g/mole

**LT-S9655** | DFHCO-4T


5,5''-Diperfluorohexylcarbonyl-2,2':5',2'':5'',2''':5''',2''''-quaterthiophene

CAS No. : 796994-57-5

Grade : Sublimed >99%

Formula : $C_{30}H_8F_{26}O_2S_4$

M.W. : 1022.6 g/mole

**LT-S9656** | Cl12BsubPc


Dodecachloro subphthalocyanatoboron(III) chloride

CAS No. : 163616-01-1

Grade : >95%

Formula : $C_{24}BCl_{13}N_6$

M.W. : 844 g/mole

**LT-S9657** | F12BsubPc


Dodecafluoro subphthalocyanatoboron(III) chloride

CAS No. : 142710-55-2

Grade : >95%

Formula : $C_{24}BClF_{12}N_6$

M.W. : 646.54 g/mole

**LT-S9663**


2,5-Bis[4-(4-phenylphenyl)phenyl]thiophene

CAS No. : 1257544-69-6

Grade : Sublimed >99%

Formula : $C_{40}H_{28}S$

M.W. : 540.72 g/mole

**LT-S9668** | F6-SubPC-Cl


Hexafluoro boron subphthalocyanine chloride

Grade : >95%

Formula : $C_{24}H_6BClF_6N_6$

M.W. : 538.6 g/mole

UV : 552 nm

**LT-S9669** | BP1T-CN


2,5-Bis(4'-cyanobiphenyl-4-yl)thiophene

CAS No. : 868403-91-2

Grade : Sublimed >99%

Formula : $C_{30}H_{18}N_2S$

M.W. : 438.54 g/mole

**LT-S9681** | DCV4T-Et2


2,2'-(3,3''-Diethyl-[2,2':5',2'':5'',2''':5''',2''''-quaterthiophene]-5,5''-diyl)bis(methanylylidene)dimalononitrile

CAS No. : 1449383-43-0

Grade : Sublimed >99%

Formula : $C_{28}H_{18}N_4S_4$

M.W. : 538.73 g/mole



LT-S9684


5,12-Di([1,1'-biphenyl]-4-yl)-naphthalene

CAS No. : 272459-50-4

Grade : Sublimed >98%

Formula : $C_{42}H_{28}$

M.W. : 532.67 g/mole




LT-S9685

5,12-Di(thiophen-2-yl)tetracene

Grade : Sublimed >98%

Formula : $C_{26}H_{16}S_2$

M.W. : 392.54 g/mole




LT-S9686

6,13-Bis(benzo[b]thiophen-2-yl)pentacene

Grade : Sublimed >98%

Formula : $C_{38}H_{22}S_2$

M.W. : 542.71 g/mole



LT-S9687


6,13-Di(2'-thienyl)pentacene

CAS No. : 849466-79-1

Grade : Sublimed >98%(NMR)

Formula : $C_{30}H_{18}S_2$

M.W. : 442.59 g/mole




LT-S9688 TBA-An

9,10-Bis([1',3'-diphenyl]-5'-phenylethynyl)anthracene

Grade : >99%

Formula : $C_{54}H_{34}$

M.W. : 682.85 g/mole



LT-S9689 3PV-CF3


1,4-Bis[4-(trifluoromethyl)styryl]benzene

CAS No. : 955092-98-5

Grade : >99%

Formula : $C_{24}H_{16}F_6$

M.W. : 418.37 g/mole




LT-S9697 F-F12BsubPc

Dodecafluoro subphthalocyanatoboron(III) fluoride

Grade : >95%

Formula : $C_{24}BF_{13}N_6$

M.W. : 630.09 g/mole




LT-S9698 PhO-F6BsubPc

Phenoxy-hexafluoro boronsubphthalocyanine

Grade : >98%

Formula : $C_{30}H_{11}BF_6N_6O$

M.W. : 596.25 g/mole



LT-S9699 PhO-BsubPc


Phenoxysubphthalocyanine boron

CAS No. : 182575-04-8

Grade : >98%

Formula : $C_{30}H_{17}BN_6O$

M.W. : 488.31 g/mole



LT-S9700 PhO-F12BsubPc


Phenoxydodecafluoro subphthalocyanatoboron

CAS No. : 464933-03-7

Grade : >98%

Formula : $C_{30}H_5BF_{12}N_6O$

M.W. : 704.19 g/mole



LT-S9701 F5PhO-F12BsubPc


Pentafluorophenoxy-Dodecafluorosubphthalocyanato boron

CAS No. : 1235758-94-7

Grade : >98%

Formula : $C_{30}BF_{17}N_6O$

M.W. : 794.14 g/mole



LT-S9702 PhO-Cl12BsubPc


Phenoxy-dodecachloro boronsubphthalocyanine

CAS No. : 1309389-84-1

Grade : >98%

Formula : $C_{30}H_5BCl_{12}N_6O$

M.W. : 901.65 g/mole



LT-S9703 | F5PhO-Cl6BsubPc


Pentafluorophenoxy-hexachloroboronsubphthalocyanine

CAS No. : 1309391-30-7

Grade : >98%

Formula : $C_{30}H_6BCl_6F_5N_6O$

M.W. : 784.93 g/mole

**LT-S9704** | F5PhO-F6BsubPc


Pentafluorophenoxy-hexafluoroboronsubphthalocyanine

CAS No. : 1680181-01-4

Grade : >98%

Formula : $C_{30}H_6BF_{11}N_6O$

M.W. : 686.2 g/mole


**LT-S9705** | F5PhO-Cl12BsubPc

Pentafluorophenoxy-dodecachloroboronsubphthalocyanine

Grade : >98%

Formula : $C_{30}BCl_{12}F_5N_6O$

M.W. : 991.6 g/mole


**LT-S9706** | F-F6BsubPc

Hexafluoro-subphthalocyanatoboron(III) fluoride

Grade : >95%

Formula : $C_{24}H_6BF_7N_6$

M.W. : 522.14 g/mole

**LT-S9708** | BP1T


2,5-Bis(4-biphenyl)thiophene

CAS No. : 56316-86-0

Grade : Sublimed >99%

Formula : $C_{28}H_{20}S$

M.W. : 388.52 g/mole

**LT-S9885** | PDI-CN2


N,N'-Bis(n-octyl)-x,y,dicyanopenylene-3,4,9,10-bis(dicarboximide), mixture of isomers

CAS No. : 862204-65-7

Grade : Sublimed >97% (mixture of isomers)

Formula : $C_{42}H_{40}N_4O_4$

M.W. : 664.79 g/mole

**LT-S9888** | NDCS


(2Z,2'Z)-2,2'-(1,4-phenylene)bis(3-(naphthalen-2-yl)acrylonitrile)

CAS No. : 1313708-82-5

Grade : Sublimed >99%

Formula : $C_{32}H_{20}N_2$

M.W. : 432.51 g/mole


**LT-S9893**

1,4-Bis((diisopropyl(octyl)silyl)ethynyl)naphthalene

Grade : >95% (NMR)

Formula : $C_{42}H_{68}Si_2$

M.W. : 629.16 g/mole

**LT-S9894** | PBNA


(2Z,2'Z)-3,3'-(1,4-phenylene)bis(2-(naphthalen-2-yl)acrylonitrile)

CAS No. : 2765079-20-5

Grade : Sublimed >99%

Formula : $C_{32}H_{20}N_2$

M.W. : 432.51 g/mole



LT-S979 | **F8T2**

Poly[(9,9-di-n-octylfluorenyl-2,7-diyl)-alt-2,2'-bithiophene-5,5'-diyl]


CAS No. : 210347-56-1

Grade : Mw > 20,000 (GPC)

Formula : (C₃₇H₄₄S₂)_n

UV : 454 nm (in THF)

PL : 500 nm (in THF)

**LT-S980** | **PQT-12**


Poly[bis(3-dodecyl-2-thienyl)-2,2'-dithiophene-5,5'-diyl]

CAS No. : 827343-06-6

Grade : Mw = 10,000~40,000 (GPC)

Formula : (C₄₀H₅₆S₄)_n

UV : 473 nm (in Toluene)

**LT-S981** | **PBTTT-C₁₂**

Poly[2,5-bis(3-dodecylthiophen-2-yl)thieno[3,2-b]thiophene]


CAS No. : 888491-18-7

Grade : Mw = 10,000~100,000 (GPC)

Formula : (C₃₈H₅₄S₄)_n

UV : 460 nm (in THF)

PL : 557 nm (in THF)

**LT-S982** | **PBTTT-C₁₄**

Poly[2,5-bis(3-tetradecylthiophen-2-yl)thieno[3,2-b]thiophene]


CAS No. : 888491-19-8

Grade : Mw = 10,000~100,000 (GPC)

Formula : (C₄₂H₆₂S₄)_n

UV : 466 nm (in THF)

PL : 557 nm (in THF)

**LT-S9060** | **PBTTT-C₁₆**


Poly[2,5-bis(3-hexadecylthiophen-2-yl)thieno[3,2-b]thiophene]

Grade : Mw = 10,000~100,000 (GPC)

Formula : (C₄₆H₇₀S₄)_n

UV : 466 nm (in THF)


PL : 557 nm (in THF)

**LT-S9091** | **TQ1**

Poly[2,3-bis-(3-octyloxyphenyl)quinoxaline-5,8-diyl-alt-thiophene-2,5-diyl]

CAS No. : 565228-37-7


Grade : Mw > 20,000 (GPC)

Formula : (C₄₀H₄₆N₂O₂S)_n**LT-S9117** | **PDQT**

Poly[2,2'-[(2,5-bis(2-octyldodecyl)-3,6-dioxo-2,3,5,6-tetrahydropyrrolo[3,4-c]pyrrole-1,4-diyl)dithiophene-5,5'-diyl-alt-2,2'-bithiophene-5,5'-diyl]

CAS No. : 1267540-03-3


Grade : Mw > 30,000 (GPC)

Formula : (C₆₂H₉₀N₂O₄S₄)_nUV : 810 nm (in CHCl₃)**LT-S9118** | **PDBT-co-TT**

Poly[2,2'-[(2,5-bis(2-octyldodecyl)-3,6-dioxo-2,3,5,6-tetrahydropyrrolo[3,4-c]pyrrole-1,4-diyl)dithiophene-5,5'-diyl-alt-thieno[3,2-b]thiophene-2,5-diyl]

CAS No. : 1444870-74-9


Grade : Mw > 30,000 (GPC)

Formula : (C₆₀H₈₈N₂O₄S₄)_nUV : 810 nm (in CHCl₃)**LT-S9119** | **PDPPBT**

Poly[2,2'-[(2,5-bis(2-octyldodecyl)-3,6-dioxo-2,3,5,6-tetrahydropyrrolo[3,4-c]pyrrole-1,4-diyl)dithieno[3,2-b]thiophene-5,5'-diyl-alt-thiophene-2,5-diyl]

CAS No. : 1270977-98-4


Grade : Mw > 30,000 (GPC)

Formula : (C₆₂H₈₈N₂O₄S₅)_nUV : 812 nm (in CHCl₃)**LT-S9133** | **PDVT-10**

Poly[3,6-dithiophen-2-yl-2,5-di(2-decyltetradecyl)-pyrrolo[3,4-c]pyrrole-1,4-dione-alt-thienylenevinylene-2,5-yl]

CAS No. : 1442682-99-6


Grade : Mw > 30,000 (GPC)

Formula : (C₇₂H₁₀₈N₂O₂S₄)_n**LT-S9155** | **PDVT-8**

Poly[3,6-dithiophen-2-yl-2,5-di(2-octyldodecyl)pyrrolo[3,4-c]pyrrole-1,4-dione-alt-thienylenevinylene-2,5-yl]

CAS No. : 1403959-01-2


Grade : Mw > 20,000 (GPC)

Formula : (C₆₄H₉₂N₂O₂S₄)_n**LT-S9178** | **PMDPP3T**

Poly[[2,5-bis(2-hexyldodecyl)-2,3,5,6-tetrahydro-3,6-dioxopyrrolo[3,4-c]pyrrole-1,4-diyl]-alt-[3',3'-dimethyl-2,2':5,2''-terthiophene]-5,5'-diyl]

CAS No. : 1429119-71-0


Grade : Mw > 30,000 (GPC)

Formula : (C₅₂H₇₆N₂O₂S₃)_nUV : 830 nm (in CHCl₃)**LT-S9282** | **P(NDI2OD-T2)**

Poly[[1,2,3,6,7,8-hexahydro-2,7-bis(2-octyldodecyl)-1,3,6,8-dioxobenzo[Imn][3,8]phenanthroline-4,9-diyl][2,2'-bithiophene]-5,5'-diyl]

CAS No. : 1100243-40-0


Grade : Mw > 10,000 (GPC)

Formula : (C₆₂H₈₈N₂O₄S₂)_n**LT-S9448** | **PNDI(2HD)2T**

Poly[[N,N'-bis(2-hexyldodecyl)naphthalene-1,4,5,8-bis(dicarboximide)-2,6-diyl]-alt-5,5'-(2,2'-bithiophene)]

CAS No. : 1459168-70-7

Grade : Mw > 10,000 (GPC)

Formula : (C₅₄H₇₂N₂O₄S₂)_n


LT-S9449 | P(NDI2OD-2FT)

Poly[[1,2,3,6,7,8-hexahydro-2,7-bis(2-octyldodecyl)-1,3,6,8-tetraoxobenzo[Imn][3,8]phenanthroline-4,9-diyl]-(3,3'-difluoro[2,2'-bithiophene]-5,5'-diyl)]

CAS No. : 1773524-46-1

Grade : Mw > 10,000 (GPC)

Formula : (C₆₂H₈₆F₂N₂O₄S₂)_n


**LT-S9591** | PZ1

Poly[2,2'-(2Z,2'Z)-((4,4,9,9-tetrahexadecyl-4,9-dihydro-s-indaceno[1,2-b:5,6-b']dithiophene-2,7-diyl)bis(methanylylidene))bis(3-oxo-2,3-dihydro-1H-indene-2,1-diylidene))dimalononitrile-5,5'-diyl-alt-thiophen-2,5-diyl]

CAS No. : 2177247-65-1

Grade : Mw > 10,000

Formula : (C₁₁₀H₁₄₆N₄O₂S₃)_n


**LT-S9619** | PBBTCD

Poly[(4,7-bis(3-hexylthien-2-yl)-2λ452-benzo[1,2-c:4,5-c']bis[1,2,5]thiadiazole)-alt-(3,3-bis(2-ethylhexyl)-4H-cyclopenta[2,1-b:3,4-b']dithiophene)]

CAS No. : 1334032-14-2

Grade : Mw > 10,000

Formula : (C₅₁H₆₄N₄S₆)_n


**LT-S9620** | PBBTSiD

Poly[(4,7-bis(3-hexylthien-2-yl)-2λ452-benzo[1,2-c:4,5-c']bis[1,2,5]thiadiazole)-alt-(3,3'-di-n-octylsilylene-2,2'-bithiophene)]

CAS No. : 1334032-16-4

Grade : Mw > 10,000

Formula : (C₅₀H₆₄N₄S₆Si)_n


**LT-S9927** | PFIID

Poly[(E)-1,1'-bis(2-octyldodecyl)-[3,3'-biindolinylidene]-2,2'-dione-6,6'-diyl][9,9-dioctyl-9H-fluorene-2,7-diyl]

CAS No. : 2019220-88-1


Grade : MW > 10000

Formula : (C₈₅H₁₂₈N₂O₂)_n

**LT-S9981** | PTDPPTFT4


Grade : MW = 50000~90000

Formula : (C₉₀H₁₄₀N₂O₂S₆)_n

**LT-S9982** | P(g42T-2T), P(g32T-2T), g4-2T


Grade : MW > 20,000 (GPC)

Formula : (C₃₀H₃₆O₈S₄)_n

**LT-S9983** | P(g42T-TT), P(g32T-TT), g4-TT


Grade : MW > 20,000 (GPC)

Formula : (C₂₈H₃₄O₈S₄)_n

**LT-S9984** | P(g42T-T), P(4O2T-T)

Grade : >99% (monomers) Mw~20000

Formula : (C₂₆H₃₄O₈S₃)_n

**LT-S9989** | IDTBT, IDT-BT, IDT-BT-C16

polymer of 2,1,3-Benzothiadiazole-4,7-diyl-co-4,4,9,9-tetrahexadecyl-4,9-dihydro-s-indaceno[1,2-b:5,6-b']dithiophene-2,7-diyl

CAS No. : 1209012-38-3

Grade : Mw > 50000

Formula : (C₈₆H₁₃₈N₂S₃)_n

